



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
17.04.2002 Bulletin 2002/16

(51) Int Cl.7: **C08G 77/38, C08G 77/46,**
C08G 77/50

(21) Application number: **97121113.1**

(22) Date of filing: **02.12.1997**

(54) **Thickening silicones with elastomeric silicone polyethers**

Verdicken von Siliconen mit elastomeren Siliconpolyethern

Epaississement de silicones avec des polyéthersilicones élastomériques

(84) Designated Contracting States:
DE FR GB

(30) Priority: **16.12.1996 US 768064**

(43) Date of publication of application:
17.06.1998 Bulletin 1998/25

(73) Proprietor: **DOW CORNING CORPORATION**
Midland Michigan 48686-0994 (US)

(72) Inventors:
• **Schulz, William James, Jr.**
Midland, Michigan 48642 (US)

• **Zhang, Shizhong**
Midland, Michigan 48642 (US)

(74) Representative:
Sternagel, Flescher, Godemeyer & Partner
Patentanwälte
Braunsberger Feld 29
51429 Bergisch Gladbach (DE)

(56) References cited:
EP-A- 0 298 402 **EP-A- 0 501 791**
GB-A- 1 093 904 **US-A- 5 493 041**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent grant. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] This invention is directed to thickened low molecular weight siloxane fluids or solvents, in the form of silicone elastomers swollen into silicone gels and silicone pastes, which can be formed into silicone emulsions.

[0002] Cross-links are junctions of polymer strands in a three-dimensional network. They may be viewed as long-chain branches which are so numerous that a continuous insoluble network or gel is formed.

[0003] Increasingly, platinum catalyzed hydrosilylation reactions are being used to form networks. They typically involve reactions between a low molecular weight siloxane containing several $\equiv\text{Si-H}$ groups and a high molecular weight siloxane containing several $\equiv\text{Si-vinyl}$ groups or vice versa.

[0004] Attractive features of this mechanism are that (i) no by-products are formed, (ii) cross-linking sites and hence network architecture can be narrowly defined, and (iii) hydrosilylation will proceed even at room temperature to form the networks. In the mechanism, crosslinking involves addition of $\equiv\text{SiH}$ across double bonds, i.e., $\equiv\text{SiH} + \text{CH}_2=\text{CH-R} \rightarrow \equiv\text{SiCH}_2\text{CH}_2\text{-R}$; or crosslinking involves addition of $\equiv\text{SiH}$ across triple bonds, i.e., $\equiv\text{SiH} + \text{HC}\equiv\text{C-R} \rightarrow \equiv\text{SiCH}=\text{CH-R}$.

[0005] We have utilized this mechanism, but by employing some unobvious and unique modifications of the mechanism, we have been able to formulate a new range of product forms having new and unique properties and ranges of application. In particular, one unique aspect is that our silicone paste can be used to form an emulsion without the need of a surfactant. This can be of considerable value in the personal care arena where skin sensitivity due to the presence of certain surfactants can be an issue.

[0006] EP-A 298 402 discloses an organopolysiloxane-polyoxyalkylene emulsifier for polar in nonpolar liquid emulsions wherein organopolysiloxane-polyoxyalkylene polymer molecules are intentionally cross-linked, but wherein gelling should be avoided.

[0007] Our invention relates to a method of making a silicone elastomer comprising reacting in step 1:

(A) an $\equiv\text{Si-H}$ containing polysiloxane of the formula $\text{R}_3\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_3$ or the formula $(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b$ and, optionally, an $\equiv\text{Si-H}$ containing polysiloxane of the formula $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_c\text{SiR}_2\text{H}$ or an $\equiv\text{Si-H}$ containing polysiloxane of the formula $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_2\text{H}$, where R, R' and R'' are alkyl groups with 1-6 carbon atoms, a is 0-250, b is 1-250 and c is 0-250; and

(B) a mono-alkenyl polyether of the formula $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{O}(\text{CH}_2\text{CH}_2\text{O})_y(\text{CH}_2\text{CH}_2\text{CHO})_z\text{T}$ or the formula $\text{CH}_2=\text{CH-Q-O}(\text{CH}_2\text{CH}_2\text{O})_y(\text{CH}_2\text{CH}_2\text{CHO})_z\text{T}$, where T is hydrogen, a $\text{C}_1\text{-C}_{10}$ alkyl group, an aryl group or a $\text{C}_1\text{-C}_{20}$ acyl group; Q is a divalent linking group containing unsaturation; x is 1-6, y is zero or 1-100; and z is zero or 1-100; provided y and z are both not zero; in the presence of a platinum catalyst, until an $\equiv\text{Si-H}$ containing polysiloxane with polyether groups is formed, whereby the range for the molar ratio of the polyether to the $\equiv\text{Si-H}$ in the $\equiv\text{Si-H}$ containing polysiloxane is 0.05 to 0.6; and reacting in step 2:

(C) the $\equiv\text{Si-H}$ containing polysiloxane with polyether groups with;

(D) an unsaturated hydrocarbon selected from alpha, omega-dienes of the formula $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{CH}=\text{CH}_2$, alpha, omega-diynes of the formula $\text{CH}\equiv\text{C}(\text{CH}_2)_x\text{C}\equiv\text{CH}$ and alpha, omega-ene-yne of the formula $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{C}\equiv\text{CH}$, where x is 1-20; in the presence of

(E) a solvent selected from (i) organic compounds, (ii) compounds containing a silicon atom, (iii) mixtures of organic compounds, (iv) mixtures of compounds containing a silicon atom, and (v) mixtures of organic compounds and compounds containing a silicon atom; and in the presence of a platinum catalyst, until a silicone elastomer is formed by crosslinking and addition of $\equiv\text{SiH}$ across double or triple bonds in the unsaturated hydrocarbon.

[0008] As another feature of our invention, additional solvent is added to the silicone elastomer and the solvent and silicone elastomer are sheared until a silicone paste is formed.

[0009] As a further feature of our invention, water is added to the silicone paste and the water and silicone paste are sheared until a silicone emulsion is formed. The silicone emulsion is formed free of the presence of a surfactant.

[0010] Silicone elastomers, silicone pastes and silicone emulsions, prepared according to these methods, have particular value and utility in treating hair, skin or underarm areas of the human body. In addition, the silicone elastomers, silicone pastes and silicone emulsions, are capable of forming barrier films after evaporation of any solvent or volatile component.

[0011] Our invention, and the various steps carried out according to our process, can be illustrated with reference to the procedure as shown below.

Step 1: Incorporation of the polyether

$\equiv\text{SiH}$ siloxane + mono-alkenyl polyether + platinum catalyst $\rightarrow \equiv\text{SiH}$ siloxane with polyether groups

Step 2: Gelation

$\equiv\text{SiH}$ siloxane with polyether group + $\equiv\text{SiH}$ siloxane (optional) + alpha, omega-diene + low molecular weight siloxane fluid + platinum catalyst \rightarrow gel (elastomer)

Step 3: Shearing and swelling

g/l elastomer + low molecular weight siloxane fluid → paste

Step 4: Emulsification

silicone paste + water + shear → silicone emulsion

[0012] In Step 1, the molar ratio of the polyether to the $\equiv\text{SiH}$ in the $\equiv\text{SiH}$ siloxane is 0.05-0.60, preferably 0.10 - 0.60.

[0013] In Step 2, the weight ratio of the low molecular weight siloxane fluid to the weight of the $\equiv\text{SiH}$ siloxane with polyether groups and the alpha, omega-diene can be from 1-98, but preferably is between 3-10. The molar ratio of the $\equiv\text{SiH}$ siloxane with polyether groups and the alpha, omega-diene can be from 20:1 to 1:20, but preferably is 1:1. While Step 2 can include a mixture of various types of compounds, at least one $\equiv\text{SiH}$ containing siloxane must include a polyether group.

[0014] For example, one formulation found especially suitable for Step 2 is a mixture containing the following compounds:

$\text{Me}_3\text{SiO}(\text{Me}_2\text{SiO})_{50}[\text{MeQSiO}]_4(\text{MeHSiO})_5\text{SiMe}_3$
 $\text{HSiMe}_2\text{O}(\text{Me}_2\text{SiO})_{10}\text{SiHMe}_2$, $\text{Me}_3\text{SiO}(\text{Me}_2\text{SiO})_8(\text{MeHSiO})_4\text{SiMe}_3$, 1,5-hexadiene and decamethylcyclopentasiloxane. In these formulas, Me is methyl and Q is $-\text{CH}_2\text{CH}_2\text{CH}_2(\text{CH}_2\text{CH}_2\text{O})_{10}\text{H}$.

[0015] In Step 3, the silicone paste should contain 80-98 percent by weight of the low molecular weight siloxane fluid or other fluid or solvent to be thickened.

[0016] In Step 4, the weight ratio of water to the silicone paste can be 95:5 to 5:95.

[0017] The $\equiv\text{Si-H}$ containing polysiloxane is represented by compounds of the formula $\text{R}_3\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_3$ referred to as type A¹ and compounds of the formula $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_c\text{SiR}_2\text{H}$ or compounds of the formula $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_2\text{H}$ referred to as type A². In the three formulas, R, R' and R'' are alkyl groups with 1-6 carbon atoms; a is 0-250; b is 1-250; and c is 0-250. The molar ratio of compounds A²:A¹ is 0-20, preferably 0-5. In preferred embodiments, compounds of types A¹ and A² are used in the reaction, however, it is possible to successfully conduct the reaction using only compounds of type A¹.

[0018] The $\equiv\text{Si-H}$ containing polysiloxane A¹ can also comprise an alkylhydrogen cyclosiloxane or an alkylhydrogen-dialkyl cyclosiloxane copolymer, represented by the formula $(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b$ where R', R'', a and b are as defined above. Preferably, a is 0-7; and b is 3-10. Some representative compounds are $(\text{OSiMeH})_4$, $(\text{OSiMeH})_3(\text{OSiMeC}_6\text{H}_{13})$, $(\text{OSiMeH})_2(\text{OSiMeC}_6\text{H}_{13})_2$ and $(\text{OSiMeH})(\text{OSiMeC}_6\text{H}_{13})_3$, where Me is $-\text{CH}_3$.

[0019] The most preferred unsaturated hydrocarbon is an alpha, omega-diene of the formula $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{CH}=\text{CH}_2$ where x is 1-20. Some representative examples of suitable alpha, omega-dienes for use herein are 1,4-pentadiene; 1,5-hexadiene; 1,6-heptadiene; 1,7-octadiene; 1,8-nonadiene; 1,9-decadiene; 1,11-dodecadiene; 1,13-tetradecadiene and 1,19-eicosadiene.

[0020] However, other unsaturated hydrocarbons can be used such as alpha, omega-diynes of the formula $\text{CH}\equiv\text{C}(\text{CH}_2)_x\text{C}\equiv\text{CH}$; or alpha, omega-ene-yne of the formula $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{C}\equiv\text{CH}$ where x is 1-20. Some representative examples of suitable alpha, omega-diynes for use herein are 1,3-butadiyne $\text{HC}\equiv\text{C}-\text{C}\equiv\text{CH}$ and 1,5-hexadiyne (dipropargyl) $\text{HC}\equiv\text{C}-\text{CH}_2\text{CH}_2-\text{C}\equiv\text{CH}$. One representative example of a suitable alpha, omega-ene-yne for use herein is hexene-5-yne-1 $\text{CH}_2=\text{CHCH}_2\text{CH}_2\text{C}\equiv\text{CH}$.

[0021] The reactions in Steps 1 and 2 requires a catalyst to effect the reaction between the $\equiv\text{SiH}$ containing siloxanes, the mono-alkenyl polyether and the alpha, omega-diene. Suitable catalysts are Group VIII transition metals, i.e., the noble metals. Such noble metal catalysts are described in US Patent 3,923,705. One preferred platinum catalyst is Karstedt's catalyst, which is described in US Patents 3,715,334 and 3,814,730. Karstedt's catalyst is a platinum divinyl tetramethyl disiloxane complex, typically containing about one weight percent of platinum, carried in a polydimethylsiloxane fluid or in a solvent such as toluene. The particular catalyst used in our examples was 20 μl and 200 μl portions of Karstedt catalyst as one weight percent of platinum carried in a two centistoke (mm^2/s) polydimethylsiloxane fluid. Another preferred platinum catalyst is a reaction product of chloroplatinic acid and an organosilicon compound containing terminal aliphatic unsaturation described in US Patent 3,419,593. The noble metal catalysts are used in amounts from 0.00001-0.5 parts per 100 weight parts of $\equiv\text{SiH}$ containing polysiloxane, preferably 0.00001-0.02 parts, most preferably 0.00001-0.002 parts.

[0022] The mono-alkenyl polyether is a compound of the formula $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{O}(\text{CH}_2\text{CH}_2\text{O})_y(\text{CH}_2\text{CH}_2\text{CHO})_z\text{T}$ or a compound of the formula $\text{CH}_2=\text{CH}-\text{Q}-\text{O}(\text{CH}_2\text{CH}_2\text{O})_y(\text{CH}_2\text{CH}_2\text{CHO})_z\text{T}$. In the formulas, T represents an end group which can be hydrogen; a C1-C10 alkyl group such as methyl, ethyl, propyl, butyl and decyl; an aryl group such as phenyl; or a C1-C20 acyl group such as acetyl, propionyl, butyryl, lauroyl, myristoyl and stearoyl. Q is a divalent linking group containing unsaturation such as phenylene- $-\text{C}_6\text{H}_4-$. The value of x is 1-6; y can be zero or have a value of 1-100; z can be zero or have a value of 1-100; with the proviso that y and z cannot both be zero.

[0023] The low molecular weight siloxane fluid can be (i) a low molecular weight linear or cyclic volatile methyl siloxane; (ii) a low molecular weight linear or cyclic, volatile or non-volatile, alkyl or aryl siloxane; or (iii) a low molecular weight linear or cyclic functional siloxane. Most preferred, however, is a low molecular weight linear or cyclic volatile methyl siloxane (VMS).




[0024] VMS compounds have the average unit formula $(\text{CH}_3)_a\text{SiO}_{(4-a)/2}$ where a has an average value of two to three. The compounds contain siloxane units joined by Si-O-Si bonds. Representative units are monofunctional "M" units $(\text{CH}_3)_3\text{SiO}_{1/2}$ and difunctional "D" units $(\text{CH}_3)_2\text{SiO}_{2/2}$.


[0025] The presence of trifunctional "T" units $\text{CH}_3\text{SiO}_{3/2}$ results in the formation of branched linear or cyclic volatile methyl siloxanes. The presence of tetrafunctional "Q" units $\text{SiO}_{4/2}$ results in the formation of branched linear or cyclic volatile methyl siloxanes.

[0026] Linear VMS have the formula

$(\text{CH}_3)_3\text{SiO}[(\text{CH}_3)_2\text{SiO}]_y\text{Si}(\text{CH}_3)_3$. The value of y is 0-5. Cyclic VMS have the formula $\{(\text{CH}_3)_2\text{SiO}\}_z$. The value of z is 3-8, preferably 3-6. These volatile methyl siloxanes generally have a boiling point less than 250°C . and a viscosity of 0.65-5.0 centistokes (mm^2/s).

[0027] These volatile methyl siloxanes can be represented by:






[0028] Some representative linear volatile methyl siloxanes (I) are hexamethyldisiloxane (MM) with a boiling point of 100°C., viscosity of 0.65 mm²/s and formula Me₃SiOSiMe₃; octamethyltrisiloxane (MDM) with a boiling point of 152°C., viscosity of 1.04 mm²/s and formula Me₃SiOMe₂SiOSiMe₃; decamethyltetrasiloxane (MD₂M) with a boiling point of 194°C., viscosity of 1.53 mm²/s and formula Me₃SiO(Me₂SiO)₂SiMe₃; dodecamethylpentasiloxane (MD₃M) with a boiling point of 229°C., viscosity of 2.06 mm²/s and formula Me₃SiO(Me₂SiO)₃SiMe₃; tetradecamethylhexasiloxane (MD₄M) with a boiling point of 245°C., viscosity of 2.63 mm²/s and formula Me₃SiO(Me₂SiO)₄SiMe₃; and hexadecamethylheptasiloxane (MD₅M) with a boiling point of 270°C., viscosity of 3.24 mm²/s and formula Me₃SiO(Me₂SiO)₅SiMe₃.

[0029] Some representative cyclic volatile methyl siloxanes (II) are hexamethylcyclotrisiloxane (D₃) a solid with a boiling point of 134°C. and formula {(Me₂SiO)}₃; octamethylcyclotetrasiloxane (D₄) with a boiling point of 176°C., viscosity of 2.3 mm²/s and formula {(Me₂SiO)}₄; decamethylcyclopentasiloxane (D₅) with a boiling point of 210°C., viscosity of 3.87 mm²/s and formula {(Me₂SiO)}₅; and dodecamethylcyclohexasiloxane (D₆) with a boiling point of 245°C., viscosity of 6.62 mm²/s and formula {(Me₂SiO)}₆.

[0030] Some representative branched volatile methyl siloxanes (III) and (IV) are heptamethyl-3-[(trimethylsilyl)oxy]trisiloxane (M₃T) with a boiling point of 192°C., viscosity of 1.57 mm²/s and formula C₁₀H₃₀O₃Si₄; hexamethyl-3,3,bis[(trimethylsilyl)oxy]trisiloxane (M₄Q) with a boiling point of 222°C., viscosity of 2.86 mm²/s and formula C₁₂H₃₆O₄Si₅; and pentamethyl [(trimethylsilyl)oxy] cyclotrisiloxane (MD₃) with the formula C₈H₂₄O₄Si₄.

[0031] Our process can also include the use of low molecular weight linear or cyclic, volatile or non-volatile, alkyl and aryl siloxanes. Representative linear siloxanes are compounds of the formula R₃SiO(R₂SiO)_ySiR₃ and representative cyclic siloxanes are compounds of the formula (R₂SiO)_z. R is an alkyl group of 2-6 carbon atoms or an aryl group such as phenyl. The value of y is 0-80, preferably 0-20. The value of z is 0-9, preferably 4-6. These siloxanes have a viscosity generally in the range of about 1-100 centistokes (mm²/s).

[0032] Other representative low molecular weight non-volatile siloxanes have the general structure:



where n has a value to provide the polymer with a viscosity in the range of about 100-1,000 centistokes (mm²/sec).

[0033] R₁ and R₂ are alkyl radicals of 2-20 carbon atoms, an aryl group such as phenyl or a functional group. Typically, the value of n is about 80-375. Illustrative siloxanes are polydiethylsiloxane, polymethylethylsiloxane, polymethylphenylsiloxane and polydiphenylsiloxane.

[0034] Low molecular weight functional siloxanes can be represented by acrylamide functional siloxane fluids, acrylate functional siloxane fluids, amide functional siloxane fluids, amino functional siloxane fluids, carbinol functional siloxane fluids, carboxy functional siloxane fluids, chloroalkyl functional siloxane fluids, epoxy functional siloxane fluids, glycol functional siloxane fluids, ketal functional siloxane fluids, mercapto functional siloxane fluids, methyl ester functional siloxane fluids, perfluoro functional siloxane fluids and silanol functional siloxane fluids.

[0035] Our invention is not limited to swelling silicone elastomers with only low molecular weight siloxane fluids. Other types of solvents can be used to swell the silicon elastomer and a single solvent or a mixture of solvents may be used.

[0036] The term for, by solvent we mean (i) organic compounds, (ii) compounds containing a silicon atom, (iii) mixtures of organic compounds, (iv) mixtures of compounds containing a silicon atom or (v) mixtures of organic compounds and compounds containing a silicon atom. This definition contemplates that the compound(s) are used on an industrial scale to dissolve, suspend or change the physical properties, of other materials.

[0037] In general, the organic compounds can be aromatic hydrocarbons, aliphatic hydrocarbons, alcohols, aldehydes, ketones, amines, esters, ethers, glycols, glycol ethers, alkyl halides or aromatic halides. Representative of some of the more common organic solvents are alcohols such as methanol, ethanol, 1-propanol, cyclohexanol, benzyl alcohol, 2-octanol, ethylene glycol, propylene glycol and glycerol; aliphatic hydrocarbons such as pentane, hexane, cyclohexane, heptane, Varnish Makers & Painters solvent (naphtha) and mineral spirits; alkyl halides such as chloroform, carbon tetrachloride, perchloroethylene, ethyl chloride and chlorobenzene; amines such as isopropylamine, cyclohexylamine, ethanolamine and diethanolamine; aromatic hydrocarbons such as benzene, toluene, ethylbenzene and xylene; esters such as ethyl acetate, isopropyl acetate, ethyl acetoacetate, amyl acetate, isobutyl isobutyrate and benzyl acetate; ethers such as ethyl ether, n-butyl ether, tetrahydrofuran and 1,4-dioxane; glycol ethers such as ethylene glycol monomethyl ether, ethylene glycol monomethyl ether acetate, diethylene glycol monobutyl ether and propylene glycol monophenyl ether; ketones such as acetone, methyl ethyl ketone, cyclohexanone, diacetone alcohol, methyl amyl ketone and diisobutyl ketone; petroleum hydrocarbons such as mineral oil, gasoline, naphtha, kerosene, gas oil, heavy oil and crude oil; lubricating oils such as spindle oil and turbine oil; and fatty oils such as corn oil, soybean oil, olive oil, rape seed oil, cotton seed oil, sardine oil, herring oil and whale oil.

[0038] Other miscellaneous organic solvents can also be used, such as acetonitrile, nitromethane, dimethylformamide, propylene oxide, trioctyl phosphate, butyrolactone, furfural, pine oil, turpentine and m-cresol.

[0039] We further intend to encompass by the term solvent, volatile flavoring agents such as oil of wintergreen; peppermint oil; spearmint oil; menthol; vanilla; cinnamon oil; clove oil; bay oil; anise oil; eucalyptus oil; thyme oil; cedar leaf oil; oil of nutmeg; oil of sage; cassia oil; cocoa; licorice; high fructose corn syrup; citrus oils such as lemon, orange, lime and grapefruit; fruit essences such as apple, pear, peach, grape, strawberry, raspberry, cherry, plum, pineapple and apricot; and other useful flavoring agents including aldehydes and esters such as cinnamyl acetate, cinnamaldehyde, eugenyl formate, p-methylanisole, acetaldehyde, benzaldehyde, anisic aldehyde, citral, nerol, decanal, vanillin, tolyl aldehyde, 2,6-dimethyloctanal and 2-ethyl butyraldehyde.

[0040] In addition, we intend the term solvent to include volatile fragrances such as natural products and perfume oils. Some representative natural products and perfume oils are ambergris, benzoin, civet, clove, leaf oil, jasmine, mate, mimosa, musk, myrrh, orris, sandalwood oil and vetiver oil; aroma chemicals such as amyl salicylate, amyl cinnamic aldehyde, benzyl acetate, citronellol, coumarin, geraniol, isobornyl acetate, ambrette and terpinyl acetate; and the various classic family perfume oils such as the floral bouquet family, the oriental family, the chypre family, the woody family, the citrus family, the canoe family, the leather family, the spice family and the herbal family.

[0041] If desired, the gel, elastomer, paste or emulsion of the present invention can be further diluted with an additional similar or dissimilar solvent(s), to form the final composition. A blend of hexane and tetrahydrofuran, a fragrance, an oil or another low molecular weight siloxane, are examples of diluents that could be so employed. Higher temperatures to speed up the process can be used.

[0042] Additional amounts of low molecular weight siloxane or solvent are added to the gel, i.e., Step 3 and the resulting mixture is subjected to shear force to form the paste. In Step 4, shear force is again used, during or after water is added to the paste to form the emulsion. Any type of mixing and shearing equipment may be used to perform these steps such as a batch mixer, planetary mixer, single or multiple screw extruder, dynamic or static mixer, colloid mill, homogenizer, sonolator or a combination thereof.

[0043] Typically, we carry out the process using approximately a 1:1 molar ratio of the $\equiv\text{Si-H}$ containing siloxane with polyether groups and the alpha, omega-diene. It is expected that useful materials may also be prepared by carrying out the process with an excess of either the $\equiv\text{Si-H}$ containing siloxane or the alpha, omega-diene, but this would be considered a less efficient use of the materials. The remainder of the composition comprises the low molecular weight siloxane or solvent, in amounts generally within the range of 65-98 percent by weight of the composition, but preferably 80-98 percent by weight.

[0044] The following examples illustrate our invention in more detail. All viscosities were measured at 25°C unless otherwise stated.

Example 1

[0045] 100 g of an organopolysiloxane with the average structure $\text{Me}_3\text{SiO}(\text{M}_2\text{SiO})_{93}(\text{MHSiO})_6\text{SiMe}_3$ and 6.07 g $\text{CH}_2=\text{CHCH}_2\text{O}(\text{CH}_2\text{CH}_2\text{O})_7\text{H}$ were mixed with 100 g 2-propanol in a three-neck round bottom flask. To this solution, 200 μl Karstedt catalyst (i.e., one weight percent platinum in two centistoke (mm^2/s) polydimethylsiloxane fluid) was added. The solution was stirred and heated to maintain it at approximately 70°C. After 1 hour, the three-neck flask was connected to a vacuum pump and evacuated to remove 2-propanol. A polyether branch $\text{d}\equiv\text{SiH}$ siloxane polymer was

obtained in almost quantitative yield.

[0046] 16 grams of the polyether branched $\equiv\text{SiH}$ siloxane polymer and 0.411 g 1,5-hexadiene were mixed with 65.64 g decamethylcyclopentasiloxane in a reaction vessel. 20 μl Karstedt catalyst was added while the solution was stirred. Gelation occurred within a few hours. The gel was left in the reactor overnight before 50 parts by weight of the gel were swollen by 50 parts by weight of decamethylcyclopentasiloxane under shear force. A uniform paste was obtained having a viscosity at a shear rate of 0.02 s^{-1} , of $1.82 \times 10^6\text{ cP/mPa}\cdot\text{s}$.

[0047] This uniform paste and deionized water in a 1:1 weight ratio were mixed in a glass jar with a mechanical stirrer and a white emulsion was formed with excellent aesthetics and stability. No surfactant was required to form this emulsion.

Example 2

[0048] 100 g of an organopolysiloxane with the average structure $\text{Me}_3\text{SiO}(\text{Me}_2\text{SiO})_{108}(\text{MeHSiO})_{10}\text{SiMe}_3$ and 12.42 g $\text{CH}_2=\text{CHCH}_2\text{O}(\text{CH}_2\text{CH}_2\text{O})_{10}[\text{CH}(\text{CH}_3)\text{CH}_2\text{O}]_4\text{H}$ were mixed with 100 g 2-propanol in a three-neck round bottom flask. To this solution, 200 μl Karstedt catalyst was added. The solution was stirred and heated to maintain it at approximately 70°C . After 1 hour, the three-neck flask was connected to a vacuum pump and evacuated to remove 2-propanol. A polyether branched $\equiv\text{SiH}$ siloxane polymer was obtained in almost quantitative yield.

[0049] 12 grams of the polyether branched $\equiv\text{SiH}$ siloxane polymer and 0.72 g 1,9-decadiene were mixed with 65.64 g decamethylcyclopentasiloxane in a reaction vessel. 20 μl Karstedt catalyst was added while the solution was stirred. Gelation occurred within a few hours. The gel was left in the reactor overnight before 50 parts by weight of the gel were swollen by 26 parts by weight of decamethylcyclopentasiloxane under shear force. A uniform paste was obtained having a coefficient of viscosity at a shear rate per second of 0.02 s^{-1} , of $2.66 \times 10^6\text{ cP/mPa}\cdot\text{s}$.

[0050] This uniform paste and deionized water in a 1:1 weight ratio were mixed in a glass jar with a mechanical stirrer and a white emulsion was formed with excellent aesthetics and stability. The emulsion had a viscosity at a shear rate of 0.02 s^{-1} , of $4.93 \times 10^6\text{ cP/mPa}\cdot\text{s}$. Again, no surfactant was required to form this emulsion.

Example 3

[0051] 100 g of an organopolysiloxane with the average structure $\text{Me}_3\text{SiO}(\text{Me}_2\text{SiO})_{93}(\text{MeHSiO})_6\text{SiMe}_3$ and 7.99 g $\text{CH}_2=\text{CHCH}_2\text{O}(\text{CH}_2\text{CH}_2\text{O})_7\text{H}$ were mixed with 100 g 2-propanol in a three-neck round bottom flask. To this solution, 200 μl Karstedt catalyst was added. The solution was stirred and heated to maintain it at approximately 70°C . After 1 hour, the three-neck flask was connected to a vacuum pump and evacuated to remove 2-propanol. A polyether branched $\equiv\text{SiH}$ siloxane polymer was obtained in almost quantitative yield.

[0052] 12 grams of the above polyether branched $\equiv\text{SiH}$ siloxane polymer, 1.5 g of a siloxane with the average structure $\text{Me}_3\text{SiO}(\text{Me}_2\text{SiO})_{16}(\text{MeHSiO})_{39}\text{SiMe}_3$ and 0.925 g 1,5-hexadiene were mixed with 84.8 g decamethylcyclopentasiloxane in a reaction vessel. 20 μl Karstedt catalyst was added while the solution was stirred. Gelation occurred within a few hours. The gel was left in the reactor overnight before 75 parts by weight of the gel were swollen by 50 parts by weight of decamethylcyclopentasiloxane under shear force. A uniform paste was obtained having a viscosity at a shear rate of 0.02 s^{-1} , of $6.6 \times 10^5\text{ cP/mPa}\cdot\text{s}$.

[0053] This uniform paste and deionized water in a 1:1 weight ratio were mixed in a glass jar with a mechanical stirrer and a white emulsion was formed with excellent aesthetics and stability. The emulsion had a viscosity at a shear rate of 0.02 s^{-1} , of $2.7 \times 10^6\text{ cP/mPa}\cdot\text{s}$. Again, no surfactant was required to form this emulsion.

[0054] This example is illustrative of an alternate embodiment of Step 2 shown above, in which an "optional" $\equiv\text{SiH}$ siloxane is included as a component.

Example 4 - First Comparative Example

[0055] The $\equiv\text{SiH}$ containing siloxane $\text{Me}_3\text{SiO}(\text{Me}_2\text{SiO})_{93}(\text{MeHSiO})_6\text{SiMe}_3$ was crosslinked with 1,5-hexadiene in decamethylcyclopentasiloxane using the proportions and procedure in Example 1. A gel was formed and the gel was then swollen with additional decamethylcyclopentasiloxane. The result was the formation of a smooth, transparent paste. However, when the paste was mixed with water, the water could not be dispersed. This example shows the effect of omitting the mono-alkenyl functionalized polyether.

Example 5 - Second Comparative Example

[0056] A polyether branched $\equiv\text{SiH}$ siloxane polymer was prepared from 100 g $\text{Me}_3\text{SiO}(\text{Me}_2\text{SiO})_{93}(\text{MeHSiO})_6\text{SiMe}_3$ and 6.07 g $\text{CH}_2=\text{CHCH}_2\text{O}(\text{CH}_2\text{CH}_2\text{O})_7\text{H}$ using the procedure in Example 1. One gram of the above polyether branched $\equiv\text{SiH}$ siloxane polymer, 10 g of decamethylcyclopentasiloxane and 11 g of deionized water, were then mixed. The

mixture appeared to emulsify under vigorous mixing using a mechanical stirrer and a milk-like emulsion appeared to form. However, in about two hours, the emulsion separated into two phases. This shows the effect of omitting the crosslinking reaction by an alpha, omega-diene.

[0057] The silicone elastomer, silicone gel, silicone paste and silicone emulsion of our invention have particular value in the personal care arena. Because of the unique volatility characteristics of the VMS component of these compositions, they can be used alone or blended with other cosmetic fluids, to form a variety of over-the-counter (OTC) personal care products.

[0058] Thus, they are useful as carriers in antiperspirants and deodorants, since they leave a dry feel and do not cool the skin upon evaporation. They are lubricious and improve the properties of skin creams, skin care lotions, moisturizers, facial treatments such as acne or wrinkle removers, personal and facial cleansers, bath oils, perfumes, colognes, sachets, sunscreens, pre-shave and after-shave lotions, liquid soaps, shaving soaps and shaving lathers. They can be used in hair shampoos, hair conditioners, hair sprays, mousses, permanents, depilatories and cuticle coats, to enhance gloss and drying time and provide conditioning benefits.

[0059] In cosmetics, they function as leveling and spreading agents for pigments in make-ups, color cosmetics, foundations, blushes, lipsticks, lip balms, eyeliners, mascaras, oil removers, color cosmetic removers and powders. They are useful as delivery systems for oil and water soluble substances such as vitamins. When incorporated into sticks, gels, lotions, aerosols and roll-ons, the compositions impart a dry, silky-smooth, payout.

[0060] In addition, the compositions exhibit other advantageous and beneficial properties such as clarity, shelf stability and ease of preparation. Hence, they can have wide application, but especially in antiperspirants, deodorants, in perfumes as a carrier and for conditioning hair.

[0061] Our silicone elastomers, gels, pastes and emulsions, have uses beyond the personal care arena, however, including their use as a filler or insulation material for electrical cable, a soil or water barrier for in-ground stabilization or as a replacement for epoxy materials used in coil-on-plug designs in the electronics industry.

[0062] They are also useful as carrier for crosslinked silicone rubber particles. In that application, (i) they allow ease of incorporation of the particles into such silicone or organic phases as sealants, paints, coatings, greases, adhesives, antifoams and potting compounds; and (ii) they provide for modifying rheological, physical or energy absorbing properties of such phases in either their neat or finished condition.

[0063] In addition, our silicone elastomers, gels, pastes and emulsions, are capable of functioning as carriers for pharmaceuticals, biocides, herbicides, pesticides and other biologically active substances; and they can be used to incorporate water and water-soluble substances into hydrophobic systems. Examples of some water-soluble substances are salicylic acid, glycerol, enzymes and glycolic acid.

[0064] Where barrier films are required, the silicone elastomers, gels, pastes and emulsions, can be applied to the surface of a substrate, such that when the solvent or low molecular weight siloxane evaporates, it leaves behind a fine powder-like particulate film on the substrate surface.

[0065] Other variations may be made in compounds, compositions and methods described herein, without departing from the essential features of our invention. The forms of our invention are exemplary only and not intended as limitations on its scope, as defined in the appended claims.

Claims

1. A method of making a silicone elastomer comprising reacting in step 1:

(A) an $\equiv\text{Si-H}$ containing polysiloxane of the formula $\text{R}_3\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_3$ or the formula $(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b$ and, optionally, an $\equiv\text{Si-H}$ containing polysiloxane of the formula $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_c\text{SiR}_2\text{H}$ or an $\equiv\text{Si-H}$ containing polysiloxane of the formula $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_2\text{H}$, where R, R' and R'' are alkyl groups with 1-6 carbon atoms, a is 0-250, b is 1-250 and c is 0-250; and

(B) a mono-alkenyl polyether of the formula $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{O}(\text{CH}_2\text{CH}_2\text{O})_y(\text{CH}_2\text{CH}_3\text{CHO})_z\text{T}$ or the formula $\text{CH}_2=\text{CH-Q-O}(\text{CH}_2\text{CH}_2\text{O})_y(\text{CH}_2\text{CH}_3\text{CHO})_z\text{T}$, where T is hydrogen, a $\text{C}_1\text{-C}_{10}$ alkyl group, an aryl group or a $\text{C}_1\text{-C}_{20}$ acyl group; Q is a divalent linking group containing unsaturation; x is 1-6, y is zero or 1-100; and z is zero or 1-100; provided y and z are both not zero, in the presence of a platinum catalyst, until an $\equiv\text{Si-H}$ containing polysiloxane with polyether groups is formed, whereby the range for the molar ratio of the polyether to the $\equiv\text{Si-H}$ in the $\equiv\text{Si-H}$ containing polysiloxane is 0.05 to 0.6; and reacting in step 2:

(C) the $\equiv\text{Si-H}$ containing polysiloxane with polyether groups with,

(D) an unsaturated hydrocarbon selected from alpha, omega-dienes of the formula $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{CH}=\text{CH}_2$, alpha, omega-diynes of the formula $\text{CH}\equiv\text{C}(\text{CH}_2)_x\text{C}\equiv\text{CH}$ and alpha, omega-ene-yne of the formula $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{C}\equiv\text{CH}$, where x is 1-20, in the presence of

(E) a solvent selected from (i) organic compounds, (ii) compounds containing a silicon atom, (iii) mixtures of

2. Verfahren nach Anspruch 1, in dem der zweite Schritt als zusätzlichen Reaktanten (F) ein $\equiv\text{Si-H}$ -haltiges Polysiloxan der Formel $\text{R}_3\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_3$ oder der Formel $(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b$ und wahlweise ein $\equiv\text{Si-H}$ -haltiges Polysiloxan der Formel $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_c\text{SiR}_2\text{H}$ oder ein $\equiv\text{Si-H}$ -haltiges Polysiloxan der Formel $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_2\text{H}$ enthält, worin R, R' und R'' Alkylgruppen mit 1 bis 6 Kohlenstoffatomen sind, a gleich 0 bis 250 ist, b gleich 1 bis 250 ist und c gleich 0 bis 250 ist.
3. Verfahren nach einem der Ansprüche 1 und 2, das die weiteren Schritte des Zugabens zusätzlicher Mengen von Lösungsmittel(n) zu dem Siliconelastomer und Scheren des (der) Lösungsmittel und des Siliconelastomers, bis eine Siliconpaste gebildet wird, umfasst.
4. Verfahren nach Anspruch 3, das die weiteren Schritte des Zugabens von Wasser zu der Siliconpaste und Scheren des Wassers und der Siliconpaste, bis eine Siliconemulsion gebildet wird, umfasst.
5. Verfahren nach Anspruch 4, wobei die Siliconemulsion ohne Zugabe eines oberflächenaktiven Mittels gebildet wird.
6. Siliconelastomer, erhältlich nach einem Verfahren nach einem der Ansprüche 1 und 2.
7. Siliconpaste, erhältlich nach dem Verfahren nach Anspruch 3.
8. Siliconemulsion, erhältlich nach einem Verfahren nach einem der Ansprüche 4 und 5.
9. Körperpflegeprodukt, enthaltend ein Siliconelastomer nach Anspruch 6 oder eine Siliconpaste nach Anspruch 7 oder eine Siliconemulsion nach Anspruch 8.
10. Verfahren zum Bereitstellen eines Sperrfilms auf der Oberfläche eines Substrats, umfassend Aufbringen auf das Substrat eines Siliconelastomers nach Anspruch 6 oder einer Siliconpaste nach Anspruch 7 oder einer Siliconemulsion nach Anspruch 8.

Revendications

1. Procédé pour la fabrication d'un élastomère de silicone comprenant la réaction dans l'étape 1:

(A) d'un polysiloxane contenant $\equiv\text{Si-H}$ de la formule $\text{R}_3\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_3$ ou de la formule $(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b$ et facultativement d'un polysiloxane contenant $\equiv\text{Si-H}$ de la formule $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_c\text{SiR}_2\text{H}$ ou d'un polysiloxane contenant $\equiv\text{Si-H}$ de la formule $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_2\text{H}$, où R, R' et R'' sont des groupes alkyle avec 1-6 atomes de carbone, a est égal à 0-250, b est égal à 1-250 et c est égal à 0-250, et

(B) d'un mono-alcénylpolyéther de la formule $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{O}(\text{CH}_2\text{CH}_2\text{O})_y(\text{CH}_2\text{CH}_3\text{CHO})_z\text{T}$ ou de la formule $\text{CH}_2=\text{CH-Q-O}(\text{CH}_2\text{CH}_2\text{O})_y(\text{CH}_2\text{CH}_3\text{CHO})_z\text{T}$, où T est un atome d'hydrogène, un groupe alkyle en $\text{C}_1\text{-C}_{10}$, un groupe aryle ou un groupe acyle en $\text{C}_1\text{-C}_{20}$, Q est un groupe de liaison divalent contenant une insaturation, x est égal à 1-6, y est égal à zéro ou à 1-100, et z est égal à zéro ou à 1-100, à condition que y et z ne sont pas tous deux égaux à zéro, en présence d'un catalyseur de platine jusqu'à ce qu'un polysiloxane contenant $\equiv\text{Si-H}$ avec des groupes polyéther soit formé, l'intervalle pour le rapport molaire du polyéther au $\equiv\text{Si-H}$ dans le polysiloxane contenant $\equiv\text{Si-H}$ est compris entre 0,05 et 0,6, et la réaction dans l'étape 2:

(C) du polysiloxane contenant $\equiv\text{Si-H}$ avec des groupes polyéther avec,

(D) un hydrocarbure insaturé choisi parmi des alpha, oméga-diènes de la formule $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{CH}=\text{CH}_2$, des alpha, oméga-diyne de la formule $\text{CH}\equiv\text{C}(\text{CH}_2)_x\text{C}\equiv\text{CH}$ et des alpha, oméga-ène-yne de la formule $\text{CH}_2=\text{CH}(\text{CH}_2)_x\text{C}\equiv\text{CH}$, où x est égal à 1-20, en présence

(E) d'un solvant choisi parmi (i) des composés organiques, (ii) des composés contenant un atome de silicium, (iii) des mélanges de composés organiques, (iv) des mélanges de composés contenant un atome de silicium et (v) des mélanges de composés organiques et de composés contenant un atome de silicium, et en présence d'un catalyseur de platine, jusqu'à ce que soit formé un élastomère de silicone par réticulation et addition de $\equiv\text{Si-H}$ à travers des doubles ou triples liaisons dans l'hydrocarbure insaturé.

2. Procédé selon la revendication 1, dans lequel la seconde étape comprend comme corps réagissant supplémentaire (F) un polysiloxane contenant $\equiv\text{Si-H}$ de la formule $\text{R}_3\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_3$ ou de la formule $(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b$ et facultativement un polysiloxane contenant $\equiv\text{Si-H}$ de la formule $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_c\text{SiR}_2\text{H}$ ou un polysiloxane contenant $\equiv\text{Si-H}$ de la formule $\text{HR}_2\text{SiO}(\text{R}'_2\text{SiO})_a(\text{R}''\text{HSiO})_b\text{SiR}_2\text{H}$, où R, R' et R'' sont des groupes alkyle

avec 1-6 atomes de carbone, a est égal à 0-250, b est égal à 1-250 et c est égal à 0-250.

3. Procédé selon l'une quelconque des revendications 1 et 2 comprenant les étapes supplémentaires d'addition de quantités supplémentaires de solvant(s) à l'élastomère de silicone et de cisaillement du (des) solvant(s) et de l'élastomère de silicone jusqu'à ce qu'une pâte de silicone soit formée.
4. Procédé selon la revendication 3 comprenant les étapes supplémentaires d'addition d'eau à la pâte de silicone et de cisaillement de l'eau et de la pâte de silicone jusqu'à ce qu'une émulsion de silicone soit formée.
5. Procédé selon la revendication 4, dans lequel l'émulsion de silicone est préparée sans addition d'un tensioactif.
6. Elastomère de silicone pouvant être obtenu par un procédé selon l'une quelconque des revendications 1 et 2.
7. Pâte de silicone pouvant être obtenue par le procédé selon la revendication 3.
8. Emulsion de silicone pouvant être obtenue par un procédé selon l'une quelconque des revendications 4 et 5.
9. Produit pour l'hygiène personnelle comprenant un élastomère de silicone selon la revendication 6 ou une pâte de silicone selon la revendication 7 ou une émulsion de silicone selon la revendication 8.
10. Procédé de fourniture d'un film barrière sur la surface d'un substrat comprenant l'application sur le substrat d'un élastomère de silicone selon la revendication 6 ou d'une pâte de silicone selon la revendication 7 ou d'une émulsion de silicone selon la revendication 8.